



TEST REPORT

Report No : AB0038128(0) Date: 29 Aug 2022

Application No : LB022321(0)

Applicant : DEKRA TESTING AND CERTIFICATION (SHANGHAI) LTD. GUANGZHOU
BRANCH
HOUSE, NO. 3 QIYUN ROAD, SCIENCE CITY,
HUANGPU DISTRICT, GUANGZHOU,
GUANGDONG PROVINCE, 510663, P.R. CHINA

Factory : FLASHBAY ELECTRONICS
BUILDING 2, JIXUN INDUSTRIAL PARK, XINJIAO, DONG'AO VILLAGE,
SHATIAN TOWN, HUIYANG DISTRICT, HUIZHOU CITY,
GUANGDONG PROVINCE, P.R.CHINA

Sample : One (1) set of submitted sample(s) stated to be :
Description : Item Name : Travel Cups
Item No. : Espresso-EE

Date Received : 29 Jul 2022.

Test Period : 29 Jul 2022 to 05 Aug 2022.

Test Requested : Specifications and Standards for Foods, Food Additives, etc. (Under the Japan Food
Sanitation Law, Ministry of Health and Welfare **notice No. 370**,
28 December 1959, the Ministry of Health, Labour and Welfare **notice No. 201**, 31
March 2006, **notice No. 416**, 11 August 2008, **notice No. 595**, 28 December 2012 and
notice No. 245, Jun 2016)
Part III – Implements, Containers and Packaging

Test Method : As stated in the above specification.

Test Result : Refer to the results pages for details.

For and on behalf of
CMA Industrial Development Foundation Limited

Authorized Signature : _____

Wan Leong Hang
Deputy Manager

Page 1 of 7

The conformity statement stated in Conclusion above is based on the decision rule agreed with applicant and listed in www.cmateesting.org/qac/statement-of-conformity.pdf.
This document is issued subject to the latest CMA Testing General Terms and Conditions of Testing and Inspection Services, available on request or accessible at website www.cmateesting.org.
This document shall not be reproduced except in full without written approval by CMA Testing. The results apply to the sample as received unless otherwise specified. The observations and test results in this report are relevant only to the sample tested.

CMA Industrial Development Foundation Limited

Room 1302, Yan Hing Centre, 9-13 Wong Chuk Yeung St., Fo Tan, Shatin, N.T., Hong Kong.

Tel: (852) 2698 8198 Fax: (852) 2695 4177 E-mail: info@cmateesting.org Web Site: <http://www.cmateesting.org>



TEST REPORT

Report No : AB0038128(0)

Date: 29 Aug 2022

Application No : LB022321(0)

Conclusion	Test Item	Result
	Specifications and Standards for Foods, Food Additives, etc. (Under the Japan Food Sanitation Law, Ministry of Health and Welfare notice No. 370 , 28 December 1959, the Ministry of Health, Labour and Welfare notice No. 201 , 31 March 2006, notice No. 416 , 11 August 2008, notice No. 595 , 28 December 2012 and notice No. 245 , Jun 2016) Part III – Implements, Containers and Packaging	Passed
Remark	Material information in this report is provided by client	

For and on behalf of
CMA Industrial Development Foundation Limited

Authorized Signature :

Wan Leong Hang
Deputy Manager

Page 2 of 7

The conformity statement stated in Conclusion above is based on the decision rule agreed with applicant and listed in www.cmateesting.org/qac/statement-of-conformity.pdf.
This document is issued subject to the latest CMA Testing General Terms and Conditions of Testing and Inspection Services, available on request or accessible at website www.cmateesting.org.
This document shall not be reproduced except in full without written approval by CMA Testing. The results apply to the sample as received unless otherwise specified. The observations and test results in this report are relevant only to the sample tested.

CMA Industrial Development Foundation Limited

Room 1302, Yan Hing Centre, 9-13 Wong Chuk Yeung St., Fo Tan, Shatin, N.T., Hong Kong.

Tel: (852) 2698 8198 Fax: (852) 2695 4177 E-mail: info@cmateesting.org Web Site: <http://www.cmateesting.org>

TEST REPORT

Report No : AB0038128(0)

Date: 29 Aug 2022

Application No : LB022321(0)

Test Result :

Specifications and Standards for Foods, Food Additives, etc. (Under the Japan Food Sanitation Law, Ministry of Health and Welfare **notice No. 370**, 28 December 1959, the Ministry of Health, Labour and Welfare **notice No. 201**, 31 March 2006, **notice No. 416**, 11 August 2008, **notice No. 595**, 28 December 2012 and **notice No. 245**, Jun 2016)

Part III - Implements, Containers and Packaging.

A. Standards for General Implements, Containers, Packaging and Component Materials

(a) Coloring matters

<u>Test item</u>	<u>1</u>	<u>2</u>	<u>Sample</u> <u>3</u>	<u>4</u>	<u>Limit</u>
Running of coloring matters	N.R.	N.R.	N.R.	N.R.	N.R.

Note 1 : N.R. denotes Not Recognized

Note 2 : Sample 1 = Black PP of lid, mouthpiece of cup
 Sample 2 = Black TPR of lid of cup
 Sample 3 = Black silicone rubber of lid of cup
 Sample 4 = Silvery stainless steel of body of cup

(b) Manufactured or Repaired using Metal

<u>Test item</u>	<u>Sample</u> <u>4</u>	<u>Limit</u>
Lead Content (% w/w)	<0.0015	0.1
Antimony (% w/w)	<0.01	5

Note 1 : % w/w denotes percentage by weight

Note 2 : < denotes less than

Note 3 : Sample 4 = Silvery stainless steel of body of cup

TEST REPORT

Report No : AB0038128(0)

Date: 29 Aug 2022

Application No : LB022321(0)

Test Result :

D. Material-specific Specifications for Implements, Containers, Packaging and Component Materials

D2. Synthetic resin implements, containers and packaging

(a) General specification

(i) Material Test

<u>Test item</u>	<u>Sample</u> <u>1</u>	<u>Limit</u>
Cadmium content (µg/g)	<5	100
Lead content (µg/g)	<15	100

(ii) Elution Test

<u>Test item</u>	<u>Sample</u> <u>1</u>	<u>Limit</u>
Consumption of KMnO ₄ (water, 60°C, 30 mins), (µg/ml)	<2	10
Heavy metals as Lead (4% acetic acid, 60°C, 30 mins), (µg/ml)	<1	1

Note 1 : µg/g denotes microgram per gram

µg/ml denotes microgram per milliliter

Note 2 : < denotes less than

Note 3 : Tests are for container / implement used at temperature less than 100°C

Note 4 : Sample 1 = Black PP of lid, mouthpiece of cup



TEST REPORT

Report No : AB0038128(0)

Date: 29 Aug 2022

Application No : LB022321(0)

Test Result :

(b) Individual specifications

Polyethylene (PE) and Polypropylene (PP)

Elution Test

<u>Test item</u>	<u>Sample 1</u>	<u>Limit</u>
Evaporation residue		
- water (60°C, 30 mins), (µg/ml)	<10	30
- 4% acetic acid (60°C, 30 mins), (µg/ml)	<10	30
- n-heptane (25°C, 60 mins), (µg/ml)	<10	150

Note 1 : µg/ml denotes microgram per milliliter

Note 2 : < denotes less than

Note 3 : Tests are for container / implement used at temperature less than 100°C

Note 4 : Sample 1 = Black PP of lid, mouthpiece of cup

TEST REPORT

Report No : AB0038128(0)

Date: 29 Aug 2022

Application No : LB022321(0)

Test Result :

D3. Rubber implements, containers and packaging

Rubber implements (except nursing utensils), containers and packaging - Not containing chlorine

<u>Test item</u>		<u>Sample</u>		<u>Limit</u>
		<u>2</u>	<u>3</u>	
(i) Material Test				
Cadmium	(µg/g)	<5	<5	100
Lead	(µg/g)	<15	<15	100
(ii) Elution Test				
Evaporation residue				
- water, 60°C, 30 mins	(µg/ml)	<10	<10	60
Phenol (water, 60°C, 30 mins)	(µg/ml)	<0.5	<0.5	5
Formaldehyde (water, 60°C, 30 mins)		NDC	NDC	NDC
Zinc (4% acetic acid, 60°C, 30 mins)	(µg/ml)	<0.1	<0.1	15
Heavy metals as Lead	(µg/ml)	<1	<1	1
(4% acetic acid, 60°C, 30 mins)				

Note 1 : µg/g denotes microgram per gram

µg/ml denotes microgram per milliliter

Note 2 : NDC denotes Not Darker than Contrast solution

Note 3 : < denotes less than

Note 4 : Tests are for container / implement used at temperature less than 100°C

Note 5 : Sample 2 = Black TPR of lid of cup

Sample 3 = Black silicone rubber of lid of cup

TEST REPORT

Report No : AB0038128(0)

Date: 29 Aug 2022

Application No : LB022321(0)

Appendix



(A)



(B)



(C)

***** End of Report *****